

surfaceform

Chamois Marmorino Data Sheet

Recommended Use:

For high quality decoration on domestic and commercial buildings.
Suitable for interior and exterior use.

Ingredients

Aged finely filtered slaked lime putty
Special powdered marble and quartz granules
Cellulose fibres
Water and acrylic binder (less than 3% total in wet volume).

Physical characteristics:

Can be polished to a semi-shine, pitted, dragged or in a pressed texture with a cloudy appearance. The feel of chamois can be made evident to the touch
Ready to use premixed white plaster
Natural anti-mould and mildew
Very high adhesion to support
Good for reducing cracks due to fibre content.

Colour

Endless variety of colours and options available, consult with Surfaceform for samples.

Fire, Smoke & Explosive hazards

Fire Growth Rate Index-04: Class O British and Class B Euroclass
Smoke Growth Rate Index: Class O British and Class B Euroclass
Non combustible material.
Tests carried out in accordance with BSEN 13823:2002

Toxicity including VOC:

0g voc per litre in white colour.
20g voc per litre if coloured using our colour additives.

Skin absorption

Keep out of reach of children. Lime products are caustic. In case of contact with skin, rinse thoroughly with water. Skin protection is recommended.

Head Office

A19 Kilcronagh Business Park
Cookstown
Northern Ireland. BT80 9HG
T +44 (0)28 8676 9607

London Office

2nd Floor
145-157 St John Street
London. EC1V 4PY
T 0845 519 4076

Email

info@surfaceform.com

Website

www.surfaceform.com

Eye absorption

Avoid contact with eyes at all times as lime products are caustic and may cause irritation. In case of contact with eyes, rinse thoroughly with water. Seek medical attention if eyes have been in contact with this product. Eye protection is recommended.

Inhalation:

A wet material with no odour or dust. Remove victim to fresh air if any unusual symptoms occur.

Ingestion

Products are not suitable for human consumption. Seek medical advice if consumed.

Packaging

24 kg net plastic containers

Disposal

Product must be disposed of according to local regulations.
Containers must be recycled

Storage

Protect from frost storing upright in temperatures between 5 and 30 degrees C.

Mixing

Water on the surface is normal, and should be removed before mixing. If a colour is required, mix the plaster first and then add the colour and mix until a continuous shade is achieved. All lime-based products lose their viscosity when shaken, and need a period of 12-24 hours after mixing to regain their density.

Coverage

1.7kg material per meter sq.

Drying Time

Touch dry - 3 hours at 20°C
Carbonation - 48 hours at 20°C
Fully dry - 180 days

Head Office

A19 Kilcronagh Business Park
Cookstown
Northern Ireland. BT80 9HG
T +44 (0)28 8676 9607

London Office

2nd Floor
145-157 St John Street
London. EC1V 4PY
T 0845 519 4076

Email

info@surfaceform.com

Website

www.surfaceform.com

Application

Done onsite in multiple layers by hand using metallic trowels, plastic trowels and sponge floats

Thickness

0.75 – 1.25mm in 2 coats

Substrate – For external applications the substrate requires a lime based smooth plaster finish. Can be used on most internal substrates. Please refer to our substrate advice documents for full substrate details.

Shelf Life - 2 years in an unopened container

This document was created as a general guide for using Surfaceform to complete projects and to help with specifications. This is a general overview and offers no guarantee for any problems that may arise. Surfaceform or its employees will not be responsible or liable for any claim or action taken against them in relation to advice offered by this document.

Head Office

A19 Kilcronagh Business Park
Cookstown
Northern Ireland. BT80 9HG
T +44 (0)28 8676 9607

London Office

2nd Floor
145-157 St John Street
London. EC1V 4PY
T 0845 519 4076

Email

info@surfaceform.com

Website

www.surfaceform.com