

# Dragged Polished Plaster Overview



## Overview

Dragged Polished Plaster has the allure of natural stone, with a definitive direction to its texture. Ideally suited to natural earth tones, which can be enhanced with organic mineral washes giving it a very unique and warm quality.

## Recommended Use

For high quality decoration on commercial and domestic buildings. This is suitable for internal use.

## Ingredients

Aged finely filtered slaked lime putty, special powdered marble, quartz granules, water and acrylic binder (less than 3% total in wet volume).

## Physical Characteristics

This product has a random open texture contrasting against a smooth closed texture and is a matt finish. Ready to use plaster. This finish becomes stronger with age, and is naturally anti-mould and mildew. Very high adhesion to substrates.

## Colour

Select a standard colour from our colour chart or select a Ral or Pantone. Colour matching is available on request.

## Application

Applied and finished using hand held tools such as trowels, spatulas, brushes and rollers. 3-5 coats depending on desired finish. Installation at temperatures of between 10°C – 30°C.

## Programme

Finish is applied on site as late in the build as possible and may need to be protected during the completion of the project. Drying times will vary with site conditions.

## Euroclass Fire Testing

Tests carried out in accordance with BSEN 13823:2002.

Fire Growth Rate Index-04	Class B
Smoke Growth Rate Index	Class B

## USA Fire Testing

Tests carried out accordance with ASTM E 84-16.

Flame Spread Index (FSI)	0
Smoke Development Index (SDI)	10
Results Classification	Class 1 or A

## Toxicity Including VOC

0g voc per litre in white colour.  
20g voc per litre if coloured using our colour additives.

## Skin Absorption

Skin protection is recommended as lime products are caustic. In the case of contact with skin rinse thoroughly with soap and water. Keep away from children.

## Eye Absorption

Avoid contact with eyes at all times as lime products are caustic and may cause irritation. If contact occurs, rinse eyes thoroughly with water and seek medical attention. Eye protection must be worn.

## Inhalation

A wet material with no odour or dust if any unusual symptoms occur move victim to fresh air. Dust masks are recommended.

## Ingestion

Products are not suitable for human consumption. Obtain medical attention if consumed.

## Packaging

24 kg net plastic containers.

## Disposal

Products must be disposed of according to local regulations. Containers must be recycled.

## Storage

Protect from frost storing/installing at temperatures between 10°C and 30°C.

## Mixing

Water on the surface is normal, and should be removed before mixing. If a colour is required, mix the plaster first and then add the colour and mix until a continuous shade is achieved. All lime-based products lose their viscosity when shaken and need to sit for a period of 12-24 hours after mixing to regain their density.

## Coverage

2-9 kg material per meter sq.

## Drying Time

Touch dry – 3hours at 20°C  
Carbonation - 48hours at 20°C  
Fully dry – 180 days.

## Thickness

1.5 – 2.5mm (plus additional 1.25mm for the reinforcing coat if required).

## Shelf Life

2 years when unopened.

## Substrate

Please see pg2 for Substrate guidelines.

## Substrate Construction Guidelines

### **Metal Studs**

Metal stud walls are to be constructed with uprights at 300mm centers. Walls need to be constructed plumb and straight with plenty of horizontal supports. Support all 4 sides of the plasterboard sheet. Plasterboard must be fixed in two layers using 12.5mm plasterboard fixed with suitable plasterboard screws at 300mm fixing centers (minimum centers). Joints should be staggered between the two layers of plasterboard.

The aim is to achieve a very well supported solid wall with no bumps, ridges between sheets or structure movements. This information must be used in conjunction with the MF manufactures guidelines.

### **Timber Studs**

Timber stud walls need to be extra well-constructed using only good quality timbers, kiln dried and well-seasoned. We recommend uprights are at no less than 300mm centers with plenty of extra horizontal supports. Support all 4 sides of the plasterboard sheet.

We recommend that in curved areas walls are sheeted with high quality plywood to support the plasterboard.

Timber structures need to be kept dry and consideration of moisture content within the building always considered during construction. If a building is very cold or has high moisture content the stud wall can take a long time to fully dry out. Walls that are not fully dry can shrink when drying thus resulting in movement or cracks.

Plasterboard must be fixed in two layers using 12.5mm plasterboard fixed with suitable plasterboard screws at 300mm fixing centers (minimum centers). Joints should be staggered between the two layers of plasterboard.

The aim is to achieve a very well supported solid wall with no bumps, ridges between sheets, or structure movement. This information must be used in conjunction with the MF manufactures guidelines.

## Substrate Preparation

### **Dry-Lined Surfaces**

The finishes can be applied to dry-lined surfaces provided the wall is straight, plumb and solid. Joints between sheets need to be fully filled, taped with a good quality jointing compound and suitable jointing tape. All joints need to be flush and finely sanded. Angle beads need to be fitted to all external corners and openings. Expansion beads need to be fitted where relevant. Beads need to be feathered back from using a good quality jointing compound and sanded.

### **Skimmed Plasterboard**

This is suitable for our finishes provided the wall has been well constructed as detailed above; plasterboard joints are filled and taped. The walls need to be well skimmed with no bumps or ridges. Walls need to be straight and plumb. Good structures that are well plastered are essential for decorative finishes.

### **Masonry Substrates Internal**

Most rendered internal walls can have a decorative finish applied. All blockwork/concrete require plaster coats prior to our finish. Two coats of sand and cement with a fine float finish or most traditional basecoat plasters finished with a skim coat are normally sufficient. All finishes need to be completed to a high standard being straight and plumb with no trowel or float marks. These need to be fully dry as per the plaster manufactures instructions.

New builds are prone to settlement cracks and we recommend our anti-crack system is used to reduce the risk of settlement cracks appearing through the plaster surface.

### **Decorated Walls & Ceilings**

Do not use over wall paper. Remove all traces of wallpaper and paste residue. Any loose material needs to be removed, backgrounds filled and sanded. Repaired substrates need to be fully dry prior to application of our plaster finishes. Walls need to be straight with no bumps. Pre-painted walls can be coated over if the paint is well attached. Sand walls prior to all applications. Fill or replaster walls if required. Fillers and plasters need to be fully dry before application of our products. Ideally, walls and ceilings need to be structurally sound with no ridges or bumps.

### **MDF Substrates**

This is a good substrate for all our plaster finishes and an easy way to create feature panels off-site. We recommend it is primed on all sides with a good quality wood primer. This is to reduce the risk of soaking in moisture and swelling. MDF should not be subjected to any moisture before or after our finishes have been applied.

We do encourage that sheet sizes are considered and considered part of the design. MDF will always crack in the joint where sheets meet therefore a space between each sheet is required.

### **Beads**

Normal rendering and expansion beads need to be fitted to all corners and openings. These should be well fitted prior to plastering and finished flush the same as for decorating with normal paints.

### **Dust**

All dust and dirt needs to be removed prior to our applications.

### **Anticrack**

We recommended that our anti-crack systems are used on top of all substrates as it reduces the risk of cracks appearing on the surface.

*This document was created as a general guide for Surfaceform products and to help with specifications. This is a general overview and offers no guarantee for any problems that may arise. Surfaceform or its employees will not be responsible or liable for any claim or action taken against them in relation to advice offered by this document.*